

KOPR-KOTE® ANTI SEIZE

Copper Anti-Seize & Thread Lubricant

KOPR-KOTE® is a low-friction, anti-seize lubricant manufactured from a combination of micro-size copper flakes and graphite dispersed in a water resistant grease and fortified with antioxidants, plus rust and corrosion inhibitors. **KOPR-KOTE®** provides protection unequalled by competitive brands.

KOPR-KOTE® provides a shield against metal-to-metal contact, preventing seizure and corrosion. It fills irregularities and imperfections and resists welding, hardening, or setting. **KOPR-KOTE®** provides low friction and cushions impact and shock loads. Low shear between particles reduces stick-slip, allowing quick disassembly with minimum wrench torque. It will not squeeze out of the threads, gum up, or wash off.

- NSF Registered H2 (No. 120923)*
- Conforms to MIL-PRF-907F
- Conforms to RAYTHEON spec M8656839 Type II
- Service rating: -65°F (-54°C) to 1800° (982°C)
- · Contains no lead or zinc
- · Lowers friction; reduces wrench torque.
- Permits reuse of fittings; saves stud, bolt, and nut replacement.
- Not affected by contraction, expansion, or vibration.
- Will not run, drip, or settle out
- · Also available in a convenient aerosol package
- · Available in convenient aerosol form.

APPLICATIONS

KOPR-KOTE® is ideal for use on threaded connections, pump housings, flanges, studs, exhaust manifold bolts, compressor heads, autoclaves, lathe centers, etc.

*Aerosol package is not NSF Registered

PRODUCT CHARACTERISTICS

Thickener Complex Based Fluid Type Petroleum Dropping Point (ASTM D-566) 450°F (232°C)

Specific Gravity 1.21 typical Density (lb/gal) 10.1 typical

Oil Separation (ASTM D-6184) <3 WT. % LOSS @ 212°F (100°C)

Flash Point (ASTM D-92) >450°F (232°C)

<3.0

Nut-Factor* 0.15

1" B7 Studs @ 80,000 psi Contact Stress

Penetration @ 77°F 310 - 330

(ASTM D-217)

VOC

Copper Strip Corrosion 1A

(ASTM D-4048)

4-Ball (ASTM D-2596) Weld Point, kgf

Weld Point, kgf 620 Load Wear Index 125 0 g/L





Address: 2502 Elm Street | Sudbury, ON | P3E 4R6

Phone: 705-682-9900 | Email: info.mcc@mansourgroup.inc

www.mansourgroup.inc